

# BAYON Clear

Used in Pozzetta PZT600, PLS600, PL500, PL535, PL600, PL655

## BAYON Material Data

Physical	Nominal Values	Test
Specific Gravity	1.14	ASTM D792

  

Mechanical	Nominal Values	Test
Tensile Strength@Yield	300 kg.f/cmsq	ASTM D638
Tensile Elongation@Yld	5.0%	ASTM D638

  

Optical	Nominal Values	Test
Transmittance	90%	ASTM D1003
Haze	4.0%	ASTM D1003

  

Hardness	Nominal Values	Test
Rockwell (R-scale)	87	ASTM D2240

  

Electrical	Nominal Values	Test
Volume Resistivity	7x10E10	ASTM D257
Surface Resistivity	3x10E11 ohm/sq	ASTM D257



*Companies around the world trust Pozzetta to create secure environments to handle, store, and transport their valuable products.*

**pozzetta.com**

3219 south platte river drive  
englewood, colorado 80110  
303.783.3172