

Orange Polypropylene

Used in Pozzetta PM300, PM400, PM500, PM600

POLYPROPYLENE

Pozzetta Orange Polypropylene Static Dissipative Material Data

Physical	Nominal Values (English)	Test
Specific Gravity	.90 sp gr 23/23 C	ASTM D792
Mold Shrink, Linear-Flow	.015 to .018 in/in	ASTM D955

Mechanical	Nominal Values (English)	Test
Tensile Modulus	0.25 psi x 10E6	ASTM D638
Tensile Strength@Yield	4700 psi	ASTM D638
Tensile Elongation@Yld	10%	ASTM D638
Flexural Modulus	0.20 psi x 10E6	ASTM D790
Flexural Strength@Yield	6000 psi	ASTM D790

Impact	Nominal Values (English)	Test
Notched Izod Impact(73F,.125in)	1.0 ft-lb/in	ASTM D256

Hardness	Nominal Values (English)	Test
Rockwell Hardness (R-Scale)	80	ASTM D785

Thermal	Nominal Values (English)	Test
DTUL@264psi-Unannealed(.125in)	163F	ASTM D648
DTUL@66psi-Unannealed(.125in)	188F	ASTM D648
CLTE, Flow	6.7e-005 in/in/F	ASTM D696

Ignition	Nominal Values (English)	Test
Flame Rating-UL 1/16in	HB	UL 94

Companies around the world trust Pozzetta to create secure environments to handle, store, and transport their valuable products.

pozzetta.com

3219 south platte river drive
englewood, colorado 80110
303.783.3172